FORM PTO-1390 (Modified) (REV 11-2000) U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371

ATTORNEY'S DOCKET NUMBER: **8830-20**

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR): **10/069242**

INTERNATIONAL APPLICATION NO.	INTERNATIONAL FILING DATE	PRIORITY DATE CLAIMED
PCT/GB00/03424	**September 7, 2000**	**September 7, 1999**

TITLE OF INVENTION
CELL GROWTH SUBSTRATE

APPLICANT(S) FOR DO/EO/US
THOMAS GILCHRIST AND DAVID MICHAEL HEALY

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
   a. ☐ is attached hereto (required only if not communicated by the International Bureau).
   b. ☒ has been communicated by the International Bureau.
   c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
   a. ☐ is attached hereto.
   b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
   a. ☐ are attached hereto (required only if not communicated by the International Bureau).
   b. ☐ have been communicated by the International Bureau.
   c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
   d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☒ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☒ Certificate of Mailing by Express Mail
23. ☐ Other items or information:

U.S. Express Mail No. EL 931089991 US
Courtesy Copy Of the Publication of PCT/GB00/03424

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR)	INTERNATIONAL APPLICATION NO.	ATTORNEY'S DOCKET NUMBER
10/069242	PCT/GB00/03424	8830-20

24. The following fees are submitted:.	CALCULATIONS PTO USE ONLY
BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :	
☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO **$1040.00**	
☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO **$890.00**	
☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO **$740.00**	
☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) **$710.00**	
☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) **$100.00**	
ENTER APPROPRIATE BASIC FEE AMOUNT =	**$890.00**
Surcharge of **$130.00** for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).	**$0.00**

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	
Total claims	18 - 20 =	0	x $18.00	**$0.00**
Independent claims	1 - 3 =	0	x $84.00	**$0.00**
Multiple Dependent Claims **(check if applicable)**			☐	**$0.00**
TOTAL OF ABOVE CALCULATIONS =				**$890.00**
☒ Applicant claims small entity status. See 37 CFR 1.27). The fees indicated above are reduced by 1/2.				**$445.00**
SUBTOTAL =				**$445.00**
Processing fee of **$130.00** for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)). +				**$0.00**
TOTAL NATIONAL FEE =				**$445.00**
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) **(check if applicable).** ☐				**$0.00**
TOTAL FEES ENCLOSED =				**$445.00**
				Amount to be: refunded $
				charged $

a. ☒ A check in the amount of **$445.00** to cover the above fees is enclosed.

b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. **50-0573** A duplicate copy of this sheet is enclosed.

d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

DANIEL A. MONACO
Drinker Biddle & Reath LLP
One Logan Square
18th and Cherry Streets
Philadelphia, Pennsylvania 19103-6996
(215) 988-3312
(215) 988-2757 Fax

SIGNATURE

DANIEL A. MONACO
NAME

30,480
REGISTRATION NUMBER

February 22, 2002
DATE

PATENT

Attorney Docket No.: 8830-20

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re:	Patent application of Thomas Gilchrist *et al.*	
		: Group Art Unit:
Serial No:	Not yet assigned	
	(International Application No: PCT/GB00/03424)	
Filed:	Herewith	
	(International Application: Sept. 7, 2000)	: Examiner:
For:	CELL GROWTH SUBSTRATE	

PRELIMINARY AMENDMENT

Commissioner for Patents
Washington, D.C. 20231
Sir:

Kindly amend the above-identified application, without prejudice, in advance of calculating the filing fee. A mark-up of the amended claims is contained in Appendix A hereto.

In the Specification:

Insert the abstract submitted herewith on a separate page.

CERTIFICATE OF MAILING
UNDER 37 C.F.R. 1.10

EXPRESS MAIL Mailing Label Number: EL 931089991 US
Date of Deposit: February 22, 2002

I hereby certify that this correspondence, along with any paper referred to as being attached or enclosed, and/or fee, is being deposited with the United States Postal Service, "EXPRESS MAIL–POST OFFICE TO ADDRESSEE" service under 37 C.F.R. 1.10, on the date indicated above, and addressed to: Commissioner for Patents, Washington, D.C. 20231.

Signature of person mailing page:

Therese McKinley
Type or print name of person

In the Claims

Rewrite claims 3, 4, 5, 6, 8, 9, 10, 12, 14, 16 and 18 to read as follows:

3. (amended) The substrate of Claim 1, wherein said matrix has at least a portion of its surface coated with living cells.

4. (amended) The substrate of Claim 1, wherein the water-soluble glass is a phosphate glass.

5. (amended) The substrate of Claim 1, wherein said water-soluble glass comprises phosphorus pentoxide as glass former.

6. (amended) The substrate of Claim 1, wherein said glass comprises an oxide or a carbonate of an alkali metal, an alkaline earth metal or a transition metal as glass modifier.

8. (amended) The substrate of Claim 1, wherein said water-soluble glass contains a boron containing compound.

9. (amended) The substrate of Claim 1, wherein said glass has a dissolution rate ranging from substantially zero to 2.0 mg/cm^2/hour at 38°C.

10. (amended) The substrate of Claim 1, wherein said glass enables a controlled release of additives in an aqueous medium.

12. (amended) The substrate of Claim 1, wherein said water-soluble glass matrix comprises water-soluble glass fibres.

14. (amended) The substrate of Claim 1, wherein said water-soluble glass matrix comprises finely comminuted glass particles.

16. (amended) The substrate of Claim 14, wherein said glass particles have an average diameter of from 15 microns to 6 mm.

18. (amended) A method to encourage growth of living tissue by providing the substrate of Claim 1.

Please cancel Claim 17.

Remarks

Claims 1 to 16 and 18 to 19 are pending in the application. The claims have been primarily amended to reduce dependencies and more closely conform to United States practice. The specification was not amended in the international phase.

Respectfully Submitted,
THOMAS GILCHRIST ET AL

Daniel A. Monaco

DANIEL A. MONACO
Registration No. 30,480
DRINKER, BIDDLE & REATH LLP
One Logan Square
18th and Cherry Streets
Philadelphia, PA 19103-6996
Phone: (215) 988-3312
Fax: (215) 988-2757
Attorney for Applicants

APPENDIX A: Mark-up of amended claims

3. (amended) The substrate of Claim 1 [or 2], wherein said matrix has at least a portion of its surface coated with living cells.

4. (amended) The substrate of [any one of Claims] Claim 1 [to 3], wherein the water-soluble glass is a phosphate glass.

5. (amended) The substrate of [any one of Claims] Claim 1 [to 4], wherein said water-soluble glass comprises phosphorus pentoxide as glass former.

6. (amended) The substrate of [any one of Claims] Claim 1 [to 5], wherein said glass comprises an oxide or a carbonate of an alkali metal, an alkaline earth metal or a transition metal as glass modifier.

8. (amended) The substrate of [any one of Claims] Claim 1 [to 7], wherein said water-soluble glass contains a boron containing compound.

9. (amended) The substrate of [any one of Claims] Claim 1 [to 8], wherein said glass has a dissolution rate ranging from substantially zero to 2.0 $mg/cm^2/hour$ at 38°C.

10. (amended) The substrate of [any one of Claims] Claim 1 [to 9], wherein said glass enables a controlled release of additives in an aqueous medium.

12. (amended) The substrate of [any one of Claims] Claim 1 [to 11], wherein said water-soluble glass matrix comprises water-soluble glass fibres.

14. (amended) The substrate of [any one of Claims] Claim 1 [to 10], wherein said water-soluble glass matrix comprises finely comminuted glass particles.

16. (amended) The substrate of Claim 14 [or 15], wherein said glass particles have an average diameter of from 15 microns to 6 mm.

18. (amended) A method to encourage growth of living tissue by providing the substrate of [Claims] Claim 1[to 16].

CELL GROWTH SUBSTRATE

Abstract of the Disclosure

A cell culture growth substrate comprising a water soluble glass matrix adapted to sustain growth of living cells. Preferably the substrate comprises or is coated with living cells. The water-soluble glass is advantageously phosphate based and comprises glass fibres or finely comminuted particles. The invention also relates to the use of the growth substrate as an implant to replace or promote repair of damaged tissue in a patient and to a method to encourage growth of living tissue.

CELL GROWTH SUBSTRATE

The present invention provides a growth substrate for cell culture. In particular, the present invention provides a cell culture growth substrate for tissue engineering.

Tissue engineering is expected to transform orthopaedics treatments, cancer therapy and the treatment of chronic degenerative diseases. Tissue engineering concerns the provision of a graft comprising living cells or suitable substrate to sustain the growth of such cells which integrate into the patient providing expedited wound healing and repair or an alternative drug delivery or gene therapy delivery system. The tissue engineering graft may be an autograft, allograft or xenograft. Autografts are formed with the patient's own cells, cultured with a suitable growth medium or substrate. Allografts rely upon cells donated from an alternative same species source (including cadaver or foetal sources) whilst xenografts rely upon cells donated from other species.

Both allografts and xenografts may be treated to minimise autoimmune rejection of the graft following implantation.

There are numerous potential applications for tissue engineered grafts, including reconstructive surgery, orthopaedics or dental applications, burn treatments or ulcer treatments (including venous ulcers and diabetic foot ulcers). A number of tissue engineered grafts have been described in the literature (see Dutton, "Tissue Engineering", Genetic Engineering News, Vol 18, No 8, April 15, 1998).

Examples of such tissue engineered grafts include APLIGRAF (Trade Mark) which is a bilayer graft including both differentiated keratinocytes and a layer of fibroblasts in a collagen matrix. APLIGRAF has been used as a skin graft, particularly for burns, diabetic foot ulcers, excisional surgery and venous ulcers (Bender, "Healing of Difficult to Heal Wounds Using a Bilayered Skin Construct", 11th Annual Symposium on Critical Issues in Surgery-Wound Healing, Science and Technology, 3-5 December 1998, St Thomas, US Virgin Islands). Other bioengineering skin equivalents include INTEGRA (Trade Mark), a xenograft of bovine collagen, glycosaminoglycans (GAG) and silastic sheet; ALLODERM (Trade Mark), an allograft of treated cadaver skin; and DERMOGRAFT (Trade Mark), an allograft of neonatal fibroblasts on a polyglactin scaffold. Tissue engineered grafts for bone include RAINBOW (Trade Mark) of IsoTis BV which is a biomimetic coating which allows a bone-like layer to grow over metal prosthesis and serves as a scaffold

for bone growth, and also EMBARC (Trade Mark) which is a resorbable bone repair material.

Despite the numerous tissue engineering grafts currently being developed, there is still a demand for further and improved products. We have now found that water-soluble glass acts as a support or matrix for cell growth and hence the glass has utility in tissue engineering.

The present invention thus provides a cell culture growth substrate comprising a water-soluble glass matrix adapted to sustain the growth of living cells. Preferably the substrate will comprise or have at least a portion of the surface thereof coated with living cells.

In one embodiment the cell culture growth substrate is pre-seeded with living cells and hence the matrix comprises or has at least a portion of its surface coated with living cells.

In one embodiment, the cell culture growth substrate will be useful as an implant or tissue graft, i.e. is designed for implantation into a patient to replace or promote repair of damaged tissues.

The water-soluble glass matrix will of course be biocompatible. Generally, the biodegradation of the water-soluble glass following implantation of the graft into a patient will be pre-determined to be compatible with the timescale required for regrowth of the tissues concerned.

The glass present in the graft acts as a cell support matrix and will function as such in vivo. Thus the graft can be used directly in vivo to provide a temporary biodegradable scaffold which will encourage ingrowth of surrounding tissues. In other embodiments pre-seeding of the graft with a pre-selected cell type, and optionally growth of that cell type, prior to implantation may be desirable.

In an alternative embodiment, the cell culture growth substrate is intended for non-clinical purposes, for example in bio-reactor and fermentation technologies for the production of drugs and other biologically derived chemicals. Organisms usually grow with increased confluence on surfaces, and enzyme reactions (and many other biochemical reactions) are generally most efficient when the enzyme is bound to a reaction surface. Beads, sinters and fibres can be used to provide the required mechanical support, with large (productive) surface areas and additional features such as controlled inorganic micro-nutrient supply, contamination control, pH buffering and a biocompatible carrier which will allow the subsequent transfer or filtration of cells, enzymes or other components bound to its surface on completion of the reaction stage.

Conveniently the water-soluble glass matrix may be in the form of water-soluble glass fibres and reference is made to our WO-A-98/54104 which describes the production of suitable glass fibres. Whilst the glass fibres can be used in the form of individual strands,

woven (e.g. a 1 x 1 basket weave) or non-woven mats may also be produced from the fibres and used as the matrix. The individual fibres of a non-woven mat may be gently sintered together to obtain coherence of the strands. Alternatively, the fibres may be used as glass wool and this form of matrix is especially suitable where the graft requires a 3D shape.

Alternatively, the water-soluble glass matrix may be produced from finely comminuted glass particles. For example, the particles may have an average diameter of from 15 μm to 6 mm, preferably from 50μm to 6 mm. Optionally, the glass particles may be sintered together to form a porous structure into or onto which cells may be seeded and in this embodiment the glass particles will have a preferred diameter of from 53 μm to 2 mm, preferably 400 μm to 2 mm. Again, a three-dimensionally shaped graft may be produced (if necessary individually tailored to be compatible with the wound site of the patient) from the sinter. Alternatively, particles following a Fuller curve packing distribution and having a range of diameters of 0.3 mm to 5.6 mm may be used.

In a further embodiment the glass may simply be in the form of a glass sheet, which may be substantially planar or may be contoured to a required shape. Etched, ground or patterned glass sheet may be used in addition to plain surfaced glass.
The water-soluble glass preferably includes phosphorous pentoxide (P_2O_5) as the glass former.

Generally the mole percentage of phosphorous pentoxide in the glass composition is less than 85%, preferably less than 60% and especially between 30-60%.

One or more oxides or carbonates of alkali, alkaline earth and transition metals are preferably used as glass modifiers.

Generally, the mole percentage of these oxides or carbonates of alkali, alkaline earth and transition metals is less than 60%, preferably between 40-60%.

Boron containing compounds (e.g. B_2O_3) are preferably used as glass additives.

Generally, the mole percentage of boron containing compounds is less than 15% or less, preferably less than 5%.

Other compounds may also be added to the glass to modify its properties, for example SiO_2, Al_2O_3, SO_3, sulphate ions (SO_4^{2-}) or transition metal compounds (e.g. first row transition metal compounds).

Typically the soluble glasses used in this invention comprise phosphorus pentoxide (P_2O_5) as the principal glass-former, together with any one or more glass-modifying non-toxic materials such as sodium oxide (Na_2O), potassium oxide (K_2O), magnesium oxide (MgO), zinc oxide (ZnO) and calcium oxide (CaO). The rate at which the glass dissolves in fluids is determined by the glass composition, generally by the ratio of glass-modifier to glass-former and by the

relative proportions of the glass-modifiers in the glass. By suitable adjustment of the glass composition, the dissolution rates in water at 38°C ranging from substantially zero (i.e. just above zero) to 25mg/cm^2/hour or more can be designed. However, the most desirable dissolution rate R of the glass is between 0.001 and 2.0mg/cm^2/hour.

The water-soluble glass is preferably a phosphate glass, and preferably comprises a source of metal ions or boron which confer either antimicrobial protection or enhanced cell growth, or both, or which are useful trace elements. Examples include silver, copper, magnesium, zinc, iron, cobalt, molybdenum, chromium, manganese, cerium, selenium, and these metal ions can be included singly or in any combination with each other. Where silver ions are of interest, these may advantageously be introduced during manufacture as silver orthophosphate (Ag_3PO_4). The glass preferably enables controlled release of metal ions or boron and other constituents in the glass and the content of these additives can vary in accordance with conditions of use and desired rates of release, the content of silver generally being up to 5 mole %. While we are following convention in describing the composition of the glass in terms of the mole % of oxides, of halides and of sulphate ions, this is not intended to imply that such chemical species are present in the glass nor that they are used for the batch for the preparation of the glass.

The optimum rate of release of metal ions into an aqueous environment may be selected by circumstances and particularly by the specific function of the released metal ions. The invention provides a means of delivering metal ions or boron to an aqueous medium at a rate which will maintain a concentration of metal ions or boron in said aqueous medium of not less than 0.01 parts per million and not greater than 10 parts per million. In some cases, the required rate of release may be such that all of the metal added to the system is released in a short period of hours or days and in other applications it may be that the total metal be released slowly at a substantially uniform rate over a period extending to months or even years. In particular cases there may be additional requirements, for example it may be desirable that no residue remains after the source of the metal ions is exhausted or, in other cases, where the metal is made available it will be desirable that any materials, other than the metal ions itself, which are simultaneously released should be physiologically harmless. In yet other cases, it may be necessary to ensure that the pH of the resulting solution does not fall outside defined limits.

Generally, the mole percentage of these additives in the glass is less than 25%, preferably less than 10%.

The cells may be any suitable cells required for grafts. Particular mention may be made of keratinocytes, fibroblasts, chrondrocytes and the like as preferred cell types. Mention may also be made of stem cells (mesenchymal, haematopoetic, and

embryonic), Schwaan cells, keratinocytes (epithelial cells), chondrocytes, osteoblasts, endothelial cells and other fibroblasts, cardiac cells (and other myoblasts), pancreatic β cells and periodontal tissues e.g. Dentine, but the invention is not limited to these cell types alone.

Embodiments of the invention will be described with reference to the following non-limiting examples and Figs. in which:

Fig. 1

Chondrocytes forming a monolayer on a glass fibre (Example 1) as viewed by laser scanning confocal microscope.

Fig. 2

Fluorescent microscopy of HUE cells on MATT01 glass fibres (see Example 2).

Fig. 3

Fluorescent microscopy of HUE cells on MATT04 glass fibres (see Example 2).

Fig. 4

SEM picture of L929 cells on glass surface at x30 magnification (see Example 3).

Fig. 5

SEM picture of L929 cells on glass surface at x170 magnification (see Example 3).

Fig. 6

SEM picture of L929 cells on glass surface at x215 magnification (see Example 3).

Fig. 7

SEM picture of L929 cells on glass surface at x610 magnification (see Example 3).

Fig. 8

Bar chart showing cell activity vs. concentration for Ag/Mg in a PBS Extraction Vehicle (see Example 4).

Fig. 9

Bar chart showing cell activity vs. concentration for Ag/Ni in a PBS Extraction Vehicle (see Example 4).

Fig. 10

Bar chart showing cell activity vs. concentration for Ag/Zn in an MEM Extraction Vehicle (see Example 4).

Fig. 11

Bar chart showing cell activity vs. concentration for Ag/B in a PBS Extraction Vehicle (see Example 4).

Fig. 12a

Bar chart showing cell activity vs. concentration for Mg/Cu in a PBS Extraction Vehicle (see Example 4).

Fig. 12b

Bar chart showing cell activity vs. concentration for Mg/Cu in an MEM Extraction Vehicle (see Example 4).

Fig. 13

Bar chart showing cell activity vs. concentration for Mg/Ni in a PBS Extraction Vehicle (see Example 4).

Fig. 14a

Bar chart showing cell activity vs. concentration for Mg/B in a PBS Extraction Vehicle (see Example 4).

Fig. 14b

Bar chart showing cell activity vs. concentration for Mg/B in a MEM Extraction Vehicle (see Example 4).

Fig. 15a

Bar chart showing cell activity vs. concentration for Ni/Cu in a PBS Extraction Vehicle (see Example 4).

Fig. 15b

Bar chart showing cell activity vs. concentration for Ni/Cu in a MEM Extraction Vehicle (see Example 4).

Fig. 16

Bar chart showing cell activity vs. concentration for Ni/Zn in a PBS Extraction Vehicle (see Example 4).

Fig. 17a

Bar chart showing cell activity vs. concentration for Ni/B in a PBS Extraction Vehicle (see Example 4).

Fig. 17b

Bar chart showing cell activity vs. concentration for Ni/B in a MEM Extraction Vehicle.

Fig. 18

Bar chart showing cell activity vs. concentration for Cu/Zn in a MEM Extraction Vehicle.

Fig. 19

Bar chart showing cell activity vs. concentration for Cu/B in a MEM Extraction Vehicle.

Fig. 20

Bar chart showing cell activity vs. concentration for Zn/B in a PBS Extraction Vehicle.

Example 1

Introduction

Controlled Release Glass (CRG) is a phosphate-based material which degrades at a predeterminable rate. The potential for using CRG as a cartilage engineering matrix has been assessed using isolated equine chondrocytes with *in-vitro* techniques. The glass was provided in fibrous form in three different compositions. The three CRG compositions provided have shown potential as a tissue engineering substrate.

Materials and Method

A total of 200,000 chondrocytes isolated from horse articular cartilage were added to each 2 cm well in a 24 well plate. Every well contained 0.02 grams of glass fibre sample. Four different fibres F1 to F4 (diameters 20-30 μm) were analysed: F1 - containing Fe_2O_3 and NaF, F2 - containing Ce_2O_3 and Se. The composition of glasses used to form F1 to F4 are set

out below in Table 1. The culture medium (containing 10% FCS) was changed daily. At time periods of 3 days, 1 week and 2 weeks, the samples were stained using rhodamine phalloidin and oregan green for the viewing of actin and tubulin using a laser scanning confocal microscope. At the same time periods, the cell supernatant was removed and stored at -80°C until analysis on cell viability and type II collagen production could be performed. Production of type II collagen was analysed by using RT-PCR analysis on the cDNA from the chondrocyte population in contact with the glass fibres. The total RNA was prepared from the cell population by the addition of 1 ml of TRIzol (SIGMA) to the cell population for 5 minutes. After this time, the TRIzol was retrieved and stored at -80°C until RT-PCR analysis could be carried out. The RT-PCR analysis was performed by tagging with primers for collagen type II and with gapDH for cell viability.

Zymography was also performed at time periods of 4 days, 1 week and 2 weeks for detection of matrix metalloproteinases (MMP's) produced by the chondrocytes.

Table 1

BATCH RECORD SELECTION

Code	Formulation as mole%													Solution Rates		Physical Form
	Na_2O	CaO	Ag_2O	P_2O_5	MgO	K_2O	B_2O_3	MnO	Fe_2O_3	NaF	Ce_2O_3	Se	TOTAL	Annealed @ 37.5°C ($mg.cm^{-2}.hr^{-1}$)	Non-Annealed @ 37.5°C ($mg.cm^{-2}.hr^{-1}$)	
F1	25.85	17.26		46.78			5.75	1.5	1.76	1.1			100	N/A	N/A	F,C + R
F2	25.78	17.42		46.1			5.82	1.52	0.95		2.01		99.6	N/A	N/A	F,C + R
F3	25.19	17.03		45.05			5.68	1.49	0.93	0.4	1.96	2.27	100	N/A	N/A	F,R + C
F4	32		3	46	4	10	5						100	0.331	0.9614	F + R

F=fibres; C=cullet; R=rods

Results and Conclusions

Chondrocytes adhered to all three types of fibre sample. At the 3 day time period, the cells appeared to be rounded. At 1 week and 2 weeks, confocal microscopy indicated cell proliferation between all time periods. At 1 week and 2 weeks, the cells were elongated and formed a monolayer along the fibre length as can be seen in Fig. 1.

The RT-PCR analysis showed that fibres F2 and F3 were producing collagen type II up to and including the two week time period indicating that the cells retained their chondrocytic phenotype.

The zymography performed on F2 and F3 showed that the cells in contact with these fibres produced MMP2 at all three time periods, but in a greater quantity at 2 weeks than 1 week, and at 1 week than 4 days. This increase of MMP2 production is expected, as the cells were seen to have increased in number at these time periods from the confocal microscope analysis.

In conclusion, all three fibres types showed cell adherence and the chondrocytes adhered to F2 and F3 appear to retain the ability to produce type II collagen.

Example 2

Biological Evaluation of Non-woven Mat Fibres

1. Objective

Using in-vitro techniques determine:

a. The cytotoxicity of a series of five non-woven mat CRG fibres.

b. The potential of the fibres as a cell substrate matrix.

2. Scope

The test procedures apply to all fibre samples.

3. Equipment and Materials

3.1 Equipment

3.1.1 Laminar air flow hood

3.1.2 Incubator maintained at 37°C/5% carbon dioxide

3.1.3 Refrigerator at 4°C

3.1.4 Freezer at -18°C

3.1.5 Vacuum source

3.1.6 Phase contrast microscope

3.2 Materials

3.2.1 Sterile plastic-ware pipettes

3.2.2 Sterile glass pipettes

3.2.3 24 well Sterile dishes

3.2.4 Surgical grade forceps

3.2.5 Surgical grade scissors

3.2.6 Sterile Universal containers

3.2.7 L929 cell culture line (ATCC NCTC Clone 929)

3.2.8 Human Umbilical endothelial cells (primary cell source, Liverpool Women's Hospital)

3.2.9 TCPS negative control

3.2.10 CRG fibres:

D021298F1 (MATT01)

D301198F1 (MATT02)

D100299F1 (MATT03)

D161298F2 (MATT04)

D171298F2 (MATT05)

All CRG fibres were supplied non-sterile in quantities 8g-38g. The compositions of CRG fibres used (MATT01 to 05) are set out below in Table 2.

Table 2

BATCH RECORD SELECTION

Code	Formulation as mole%													Solution Rates		Physical Form
	Na_2O	CaO	Ag_2O	P_2O_5	MgO	K_2O	B_2O_3	MnO	Fe_2O_3	NaF	Ce_2O_3	Se	TOTAL	Annealed @ 37.5°C ($mg.cm^{-2}.hr^{-1}$)	Non-Annealed @ 37.5°C ($mg.cm^{-2}.hr^{-1}$)	
MATT01		27.98		46.56	19.07		6.36						99.97	N/A	N/A	R,F + C
MATT02		30		50	20								100	N/A	N/A	F,R + C
MATT03		25		50	20	5							100	0.0095	0.0151	R + F
MATT04	26.05	17.6		47.04			5.88	1.54	0.96	0.4	1		100.47	0.0143	0.0165	R + F
MATT05	25.19	17.03		45.05			5.68	1.49	0.93	0.4	1.96	2.27	100	0.0177	0.02	R + F

R=rods; F=fibres; C=cullet

4. Procedure

4.1 Test sample preparation

4.1.1 Test samples were cut to the appropriate size (see section 4.2.1).

4.1.2 Tissue culture polystyrene was employed as a negative control. The controls were not in the same physical form as the test material.

4.2 Fibres were examined in contact with the L929 cell line before any cleaning procedure. Fibres were examined in contact with both cell lines after cleaning in acetone, washing in PBS and sterilising in a dry oven at 190°C for 2 hours.

4.3 Cell preparation

4.3.1 A cell subculture was prepared 24 hours before being introduced to the fibres.

4.4 Test procedure

4.4.1 A small "bed" of the fibres was placed in the bottom of each well.

4.4.2 The cell/medium preparation was gently pipetted onto the fibre bed.

4.4.3 The 24-well plates were incubated and examined at 24 hours and 48 hours.

4.5 Interpretation of results

4.5.1 At the conclusion of the incubation period the plates are removed from the incubator and examined under phase contract microscopy using x10 and x20 objective lenses.

4.5.2 Each test and control material was initially evaluated using the scoring system detailed below. This evaluation was based on the appearance of the cells which were attached to the TCPS surface. It was not possible to carry out such an evaluation on the cells adhering to the fibres.

Table 3 : Reactivity Responses

Grade	Reactivity	Conditions of all cultures
0	None	Discrete intracytoplasmic granules; no cell lysis
1	Slight	Not more than 20% of cells are round, loosely attached and without intracytoplasmic granules; occasional lysed cells are present
2	Mild	Not more than 50% of the cells are round and devoid of intracytoplasmic granules; extensive cell lysis and empty areas between cells
3	Moderate	No more than 70% of the cell layers contain rounded cells and/or are lysed
4	Severe	Nearly complete destruction of the cell layers

4.6 Cytotoxicity Results

The following table highlights the results obtained following two separate tests. Two or four readings were taken at each test. In all cases negative control (TCPS) provided a 0 grade.

Table 4

Material Code	Grade Test 1 L9292	Material Code	Grade Test 2 L929	Test 2 HUE
MATT01	0	MATT01	0	0
MATT02	-	MATT02	0	0
MATT03	-	MATT03	-	0
MATT04	0	MATT04	0	0
MATT05	0	MATT05	0	0

Comments

The results as detailed provide a very subjective assessment of material cytotoxicity. Where a grade 0 is shown, there was no evidence of toxicity and a confluent healthy monolayer of cells was present. Where there was evidence of contamination or where the cell monolayer is difficult to evaluate no score has been given.

4.7 Cell Substrate Results

The following table (Table 5) details the cell-fibre interactions and general cell culture conditions observed by phase contrast microscopy. As stated before phase-contrast images of the cells on the fibres are poor. A staining procedure was carried out with the HUE cells. This procedure uses a fluorescent staining technique (ethidium bromide and acridene orange) to identify cell viability. All observations were after 48 hour contact between cells and fibres.

Table 5

	MATT01	MATT02	MATT03	MATT04	MATT05
L929 non-sterile fibres	Cells are viable.	Contamination	Contamination	Cells are viable. Healthy monolayer. There is some evidence of cell adhesion onto the fibres.	Cells are viable. Healthy monolayer. There is some evidence of cell adhesion onto the fibres.
L929 sterile fibres	Cells are viable but very granular. These fibres are having some adverse effect on the cells.	Culture medium pH levels are low. Cells are viable. There is no obvious cell adherence to the fibre.	pH is low. There seems to be evidence of contamination-though this may be degrading glass. Difficult to make any comment on cell viability.	Cells viable. Healthy monolayer. There is some evidence of cell adhesion onto the fibres.	Cells viable. Healthy monolayer. There is some evidence of cell adhesion onto the fibres.
HUE sterile fibres	Cells are viable though granular in appearance. The medium pH has dropped. Some cells can be seen adhering to the fibres (Fig. 2).	Cells are viable. There is no obvious cell adherence to the fibre.	pH is low. There seems to be evidence of contamination-though this may be degrading glass. Difficult to make any comment on cell viability.	Cells viable. Cell monolayer on TCPS is healthy and equivalent to the control wells. There is some evidence of cell attachment but this is difficult to observe by phase contrast. (See Fig. 3).	Cells viable. Cell monolayer on TCPS is healthy and equivalent to the control wells. There is some evidence of cell attachment but this is difficult to observe by phase contrast.

The images shown in Figs. 3 and 4 were obtained following the vital staining procedure and examined by fluorescent microscopy.

In Fig. 2 the bright areas represent viable cells (hue). The image shows an area with bundles of fibres radiating in many directions. In most cases the cells are rounded and not elongated on the fibres.

In Fig. 3 the bright areas represent viable cells (hue). Cells can be seen elongated on the fibres. In this image most of the fibres are oriented in the same direction. There is excellent cell coverage. This image is also representative of the result obtained with MATT05.

Of the five fibre compositions examined, MATT04 and MATT05 are providing an excellent substrate for cell adhesion. MATT01 has large numbers of cells adhering although the cell morphology is more rounded than that seen on the control surface. MATT02 and MATT03 show cells adhering but in much reduced numbers. There is no evidence of cytotoxicity with any of the fibres examined.

As well as demonstrating cell viability the procedure permitted a better evaluation of the cells attaching to the fibres. The cell-fibre interaction was much better than that indicated by phase contrast microscopy. It was noted that MATT04 and MATT05 had excellent cell adherence. MATT01 permitted a good cell adherence. There was cell attachment with MATT02 and MATT03

1 although this was poor in comparison with 01, 04 and
2 05.
3
4 **Example 3**
5
6 A cell suspension (in complete cell culture medium
7 supplemented with 5% foetal calf serum) at a
8 concentration of approx. 5 x 10^5 cell/ml was introduced
9 to an established mouse fibroblast cell line (L929).
10
11 The material/cell interaction was examined using phase
12 contrast microscopy at 24, 48 and 72 hours. In
13 particular the following materials were examined (see
14 Table 6 for composition of the glasses referred to by
15 batch number).
16
17 a) Glass sheet (flat); code 1051098-1
18
19 Cells can be seen adhering to the material and remain
20 in contact with the material following sequential
21 transfer between dishes. The cell morphology is
22 rounded and the growth rate is considerably slower than
23 observed with cells on the control dishes.
24 Nevertheless there is evidence of cell division taking
25 place on the surface.
26
27 b) Sintered glass beads (smooth surface); code BX-
28 D221098-1, Sintered glass beads (rough surface);
29 code BX-D221098-1
30
31 It is more difficult to make the observations with
32 these samples using phase contrast. However, cells are

clearly present on the surface of both rough and smooth samples. The cell population is certainly increasing with time up to the 72 hour period. Again, this is following sequential transfer at 24 hours.

Table 6

Batch Number	Formulation as mole%			Total	Solution Rates		Physical Form
	Na_2O	CaO	P_2O_5		Annealed @37.5°c (mg.cm'2 .hr'1	Annealed @37.5°c (mg.cm'2. hr'1	
I051098 -1	25	28	47	100	0.0991	0.1364	R+S
D221098 -1	11	42	47	100	0.0377	0.0446	G+R

G=GRANULES R=RODS S=SHEETS

Sample SEMs were obtained (see Figs. 4 to 7) after cells had been in contact with the glass for 72 hours, fixed in 2.5% glutaraldehyde and dehydrated with alcohol. The samples were gold coated before viewing. The magnification is indicated on Figs. 4 to 7.

Example 4

The potential for using CRG glass releasing two different kinds of metallic ions or boron as a cell culture growth substrate has been assessed for L929 mouse fibroblast cell line. To do so extraction vehicles were prepared which combined extracts of a mixture of two CRG's releasing a different type of metallic ions or boron, then it was determined at which concentration a positive effect on the metabolic

activity of an L929 mouse fibroblast cell line was obtained. This data would give a good indication of the potential of these combined CRG as matrix for cell growth substrates according to the invention.

Materials

The materials used in this investigation were control release glasses (CRG's) containing silver (Ag), copper (Cu), magnesium (Mg), zinc (Zn), nickel (Ni) ions and boron (B). The glasses were pre-ground to a particle size < 53 μm. The composition of the CRG's are shown in Table 7 below, along with information on dissolution rates. The extraction vehicles used were PBS (phosphate buffered solution - similar to fluids found in the body) and MEM (199 Modified Earles Medium - containing serum proteins).

Table 7

CRG Composition and Dissolution Rates

CRG	Na_2O (mol%)	CaO (mol%)	P_2O_5 (mol%)	Ion (mol%)	Dissolution Rate ($Mg/cm^2/hr$) (annealed)	Dissolution Rate ($Mg/cm^2/hr$) (non-annealed)
Ag	32	18	47	3	0.5673	0.9413
Cu	31	15	47	7	0.6608	0.9973
Mg	38	9	47	6	0.9764	1.4004
Zn	31	14	47	8	1.5638	0.9232
Ni	32	18	47	3	0.2166	0.2999
B	41.5	-	41.5	17	0.1188	0.1744

Establishing an L929 mouse fibroblast cell line

The cell line was established by subculturing an already existing cell line that was maintained by the University of Liverpool. The cells are maintained in 199 Modified Earles Medium (MEM), and stored in incubation at 37°C in a 5% CO_2/95% air atmosphere. The cells were grown to confluence in a flat-bottomed flask, and the monolayer was then harvested using trypsinization. The subculturing was carried out under sterile conditions using a laminar flow hood, and the following protocol was followed:

Fibroblast Subculturing Protocol

- Take the original flask containing 10 ml of MEM, and check the cells under the microscope.
- Place the flask under the laminar flow hood and remove the MEM using a sterile glass pasteur and vacuum.
- Add 2.5 ml of 1% trypsin to the flask to loosen the confluent layer of cells. Observe the loosening of the cells under the microscope (it takes approx 3-4 mins).
- Once the cells are loosening (they take on a rounded appearance) return the flask to the hood and remove the trypsin using a pasteur and the vacuum, replace with 10 ml of fresh MEM.
- The flask is then agitated gently to remove the cells from the base, forming a suspension of approximately 10^6 cells/ml concentration.
- 1 ml of this suspension is then added to 9 ml of fresh MEM in a fresh flask. Two flasks are prepared in this manner.
- Finally the flasks are labelled with name, date and cell line. The cells are then returned to the incubator and left for a week to establish a confluent layer of cells.

Subculturing then takes place once a week, with two subculturing flasks being prepared at a 1 in 10 concentration (then left for a week to develop a confluent layer), and the 96 well microtitre plates being prepared at a 1 in 40 concentration. The estimated cell concentration when the layer is confluent is 1 x 10^6 cells/ml.

Preparing the Extraction Vehicles

0.1 g of each of the CRG's making up the combinations was weighed out using a microbalance. The CRG's were placed into a sterile universal container and to this 20 ml of the extraction vehicle was added i.e. PBS or MEM. The extraction vehicles were then incubated at 37°C in a 5% CO_2/95% air atmosphere for a period of four hours. Four hours was selected as the CRG's had completely dissolved in the PBS within this time, and began to precipitate out if left for longer. The CRG's had still not dissolved fully when left in MEM for a period of 72 hours, and so it was decided to use four hours for both extraction vehicles. After this time they were removed from the incubator and filtered under sterile conditions. The filtering was performed to remove any contamination and precipitates.

The next step was to prepare the range of concentrations. The filtered extract (20 ml) was initially added to 20 ml of double strength culture medium to provide a starting concentration of 50% in a single strength medium. This concentration was not used during the tests. Next, 10 ml of MEM was measured out into a fresh universal container and 10 ml of 50% solution added to provide a 25% concentration, this was further diluted in MEM until a concentration of 0.05% had been established.

1. 10 ml 50.0% solution + 10 ml fresh MEM = 25.0% concentration*.

2. 10 ml 25.0% solution + 10 ml fresh MEM = 12.5% concentration*.
3. 10 ml 12.5% solution + 10 ml fresh MEM = 6.25% concentration*.
4. 10 ml 6.25% solution + 10 ml fresh MEM = 3.12% concentration.
5. 10 ml 3.12% solution + 10 ml fresh MEM = 1.60% concentration*.
6. 10 ml 1.60% solution + 10 ml fresh MEM = 0.80% concentration.
7. 10 ml 0.80% solution + 10 ml fresh MEM = 0.40% concentration*.
8. 10 ml 0.40% solution + 10 ml fresh MEM = 0.20% concentration.
9. 10 ml 0.20% solution + 10 ml fresh MEM = 0.10% concentration*.
10. 10 ml 0.10% solution + 10 ml fresh MEM = 0.05% concentration*.

* Concentrations used throughout the test.

Setting up the well plates

The well plates were seeded with a 1 in 40 concentration of fibroblasts. The medium was pipetted into the wells using a pipetter and a sterile trough. A 1 in 40 concentration was chosen as the effects on the growth of the cells was being investigated and so a confluent layer was not required.

The plates were then re-incubated at 37°C in a 5%/CO_2/95% air atmosphere) for a period of 48 hours or 96 hours. After this time, the medium was removed from the plates under sterile conditions and replaced with the prepared exudates in the following manner. Twelve wells were used for each concentration, and again the pipetter and sterile troughs were used to deliver the extraction of vehicles to the wells.

Control 12 wells	12.5% 12 wells	1.6% 12 wells	0.1% 12 wells
25% 12 wells	6.25% 12 wells	0.4% 12 wells	0.05% 12 wells

The plates were then incubated (at 37°C in a 5% CO_2/95% air atmosphere) for a further period of 48 hours or 72 hours, after which the extraction vehicle was removed and an MTT assay was performed.

Performing the MTT Assay

The MTT assay is a rapid colomeric assay based on the tetrazolium salt MTT (3- (4,5-dimethylthiazol-2-yl)-2,5-diphenyl tetrazolium bromide). The cells produce certain enzymes when they are growing, and the MTT salt solution is cleaved into blue formazan crystals by one such enzyme reportedly the "mitochondrial enzyme succinate-dehydrogenase". The crystals are soluble in iso-propranol and produce a coloured aqueous solution. The amount of formazan produced is said to be proportional to the number of viable cells present i.e.

the darker the shade of blue produced indicates a greater level of cell activity.

200 µl of MTT salt solution was added to each well in the plates at a concentration of 1 mg/ml and the plates were then incubated at 37°C for a period of four hours. The MTT solution was then removed and replaced with approximately 100 µl of iso-propranol. The plates were then incubated for a further 20 minutes (at 37°C). To ensure complete dissolution of the blue formazan crystals the plates were gently shaken.

The final stage was to measure the optical density readings of the plates using an enzyme-linked immunosorbent assay (ELISA) plate reader at a test wavelength of 570 nm.

The repetition for the results was obtained by using 12 wells in the 96 well plate for each of the concentrations and the control. Repetition was required to reduce the amount of error involved with the results.

So that the results were comparable, various different steps were taken. These included:

- The dissolution time for each extraction vehicle for four hours.
- The incubation times were the same for each exudate, either two days in MEM followed by two days with the

exudate (2d-2d), or four days in MEM followed by three days with the exudate (4d-3d).

- The cells were kept at constant conditions throughout the investigation, 37°C/5% CO_2.

The results obtained have been displayed as bar charts and are shown in Figs. 8 to 20. The important features to consider on the charts are the set numbers and the cell activity levels. Each of the set number correlates to a different concentration as follows:

Set One	:	Control
Set Two	:	25%
Set Three	:	12.5%
Set Four	:	6.25%
Set Five	:	1.6%
Set Six	:	0.4%
Set Seven	:	0.1%
Set Eight	:	0.05%

The control used throughout the study was cells at a 1 in 40 concentration proliferating in 5% MEM with added fetal calf serum and antibiotics. This control was used because it gave a good indication of the accuracy of the MTT assay, and could be easily used to determine whether the combinations were antagonising or synergising cell growth.

To obtain the cell activity level from the optical density readings the control was fixed to the level of one, the remainder of the optical density readings

obtained were then adjusted in accordance with this level. This means that by observing the charts it is easy to determine whether the combinations are having a positive or negative effect on the cell growth.

Several of the optical density readings could not be counted by the ELISA plate when the cells were left for the longer period of time. The amount of cell activity was greater than the range of the plate reader. However, these results are known to be at least three, and so have been added to the results as this minimum value. Results where this has occurred are marked with an * on the charts.

Results

Ag/Mg in a PBS Extraction Vehicle (Fig. 8)

The graph of Fig. 8 shows a stimulation response evident for the 2d-d2 sample over the range 6.25% to 0.05%, with the peak stimulation occurring at a concentration of 0.05%, exhibiting a 28% increase on the control level.

Ag/Ni in a PBS Extraction Vehicle (Fig. 9)

The graph shown in Fig. 11 shows a stimulatory effect occurring during the 2d-2d period. There is a stimulation taking place at 0.05%, and being 15% above the control. No result was obtained for 12.5% for 2d-2d as it was not initially selected in the range of concentrations.

Ag/Zn in an MEM Extraction Vehicle (Fig. 10)

There is evidence of this combination reacting toxically to the cells at high concentrations (25%, 12.5% and 6.25%) for both length of times. However, for the lowest concentrations of 0.1% and 0.05% cell proliferation has been induced. The stimulation for the shorter time period is greater than for 4d-3d, with a 17% increase on the control level at 0.05%.

Ag/B in a PBS Extraction Vehicle (Fig. 11)

The analysis of the graph represented in Fig. 11 shows that for 2d-2d periods the stimulation of the cell metabolism begins at 12.5%, with the peak occurring at 0.05%, 40% above the control. For the 4d-3d period, a stimulatory effect of 5% above the control occurs at the 0.05% concentration.

Mg/Cu in a PBS Extraction Vehicle (Fig. 12a)

The graph of Fig. 12a shows that a stimulatory response occurs for the 2d-2d time period for concentrations between 6.25% and 0.4% with a peak being displayed at 6.25%, indicating a 28% increase on the control.

Considering the ions individually, magnesium is known to be fairly non-toxic ion even in the high concentrations, however, copper ions are extremely toxic at high concentrations. This would suggest that by combining the copper with the magnesium, the

magnesium is suppressing the affect of the copper over this particular range for the PBS.

Mg/Cu in an MEM Extraction Vehicle (Fig. 12b)

The graph of Fig. 12b shows that cell proliferation occurs at the lower concentrations, (0.4%, 0.1% and 0.05%) for the 4d-3d samples. A peak occurs at 0.05% indicating a 33% increase on the control levels of cells. The 4d-3d time period also exhibits a gradual increase from toxicity to stimulation.

Mg/Ni in a PBS Extraction Vehicle (Fig. 13)

The 2d-2d time period exhibits very interesting behaviour with a stimulatory peak occurring at a concentration of 1.6%, indicating a 24% increase on cell metabolism above the control. A stimulatory response also occurs at 6.25% and 0.05%.

Mg/B in a PBS Extraction Vehicles (Fig. 14a)

This CRG combination produces a significant stimulatory effect for the 2d-2d period, with stimulation being apparent from 0.05% up to 1.6% (although 0.1% is just below the control). The peak in this positive effect occurs at a concentration of 1.6% and is 32% above the control level.

Mg/B in an MEM Extraction Vehicle (Fig. 14b)

The graph of Fig. 14b shows that there is a very small toxic effect on the metabolism of the cells in both of the chosen time periods. In fact the cell activity levels for concentrations between 25% and 1.6% are fairly equal. For the 4d-3d time, a stimulatory effect is present from 0.4% onwards. The maximum stimulation occurs at 0.05% and is 14% above the control.

Ni/Cu in a PBS Extraction Vehicle (Fig. 15a)

The graph of Fig. 15a shows high levels of toxicity occurring at the high concentrations 25% and 12.5% for both lengths of time. For the 2d-2d time there is a sudden increase in the cell activity to just 7% below the control at the 6.25% CRG concentration. Cell metabolism stimulation can be seen from 1.6% onwards for 2d-2d, and 0.4% for the 4d-3d. Both time periods peak at 0.05%, at approximately the same level 12/13%.

Ni/Cu in an MEM Extraction Vehicle (Fig. 15b)

A toxic effect can be seen at the high concentrations for both time periods as with many of the other combinations. The toxicity levels are then significantly lower at 1.6%. For the 4d-3d time there is evidence of stimulation from 0.4% through to 0.05%, with both 0.1% and 0.05% stimulating by 15% above the control. There is a sign of stimulation in the 2d-2d time at 0.1%, however, it is only 1.5% above the level of the control.

Ni/Zn in an MEM Extraction Vehicle (Fig. 16)

The main feature of the graph of Fig. 16 is the stimulation peak for the 2d-2d time at a concentration of 0.1%, 12% above the control. The stimulation peak for 4d-3d at the 0.05% concentration approximately 8% above the control, and toxic effects are present at the high concentrations. There is a sharp increase in the cell activity between 6.25% and 1.6%.

Ni/B in a PBS Extraction Vehicle (Fig. 17a)

This combination elicits a stimulatory response on the cell metabolism over the concentration range 1.6% to 0.05% for the 2d-2d with a maximum occurring at a concentration of 0.1%, 25% above the control. There is a gradual increase in the activity of the cells over the 4d-3d period, with non-toxicity being reached at 0.1%, and a peak occurring at 0.05%, 17% above the control.

Ni/B in an MEM Extraction Vehicle (Fig. 17b)

The results shown in the graph of Fig. 17b for the 2d-2d period are high toxicity at the high concentrations with a gradual increase in the cell activity over the range. There is a positive effect occurring due to this combination. There is stimulation from 12.5% onwards, peaking at 0.05%, 33% above the control.

Cu/Zn in an MEM Extraction Vehicle (Fig. 18)

The graph in Fig. 18 shows that this combination elicits a toxic response at the higher concentrations

(25% through to 6.25%). The cell growth ceases to be affected at 0.05% for the 2d-2d time. There is cell proliferation occurring in the 4d-3d set of results from 0.4% onwards. The maximum stimulation occurs at 0.05%, with a significant increase of 42% on the control level.

Cu/B in an MEM Extraction Vehicle (Fig. 19)

Considering the graph of Fig. 19, it is noticeable that there is a gradual increase in the cell activity for both 2d-2d and 4d-3d. At 25% the combination elicits a toxic effect on the cells and at 0.05% it produces cell proliferation. It is 20% above the control for 2d-2d, and 28% above the control for the 4d-3d.

Zn/B in a PBS Extraction Vehicle (Fig. 20)

Considering the graph of Fig. 20 there is evidence of toxicity at the high concentrations (25%, 12.5% and 6.25%) for both time periods. The stimulatory effect by the cells to this combination for the 2d-2d period begins at a concentration of 1.6% and peaks at 0.1%, 27% greater than the control level.

Conclusion

The results collected show that CRG releasing various combinations of metallic ions and boron have potential as a matrix in a cell culture growth substrate according to the invention. This is the case in particular for combinations containing boron where in

some combinations the stimulation is 25% greater than the control.

CLAIMS

1. A cell culture growth substrate comprising a water soluble glass matrix adapted to sustain growth of living cells.

2. The substrate of Claim 1, wherein at least a portion of the surface of said substrate is coated with living cells.

3. The substrate of Claim 1 or 2, wherein said matrix has at least a portion of its surface coated with living cells.

4. The substrate of any one of Claims 1 to 3, wherein the water-soluble glass is a phosphate glass.

5. The substrate of any one of Claims 1 to 4, wherein said water-soluble glass comprises phosphorous pentoxide as glass former.

6. The substrate of any one of Claims 1 to 5, wherein said glass comprises an oxide or a carbonate of an alkali metal, an alkaline earth metal or a transition metal as glass modifier.

7. The substrate of Claim 6, wherein said glass modifier is sodium oxide, potassium oxide, magnesium oxide, zinc oxide or calcium oxide.

8. The substrate of any one of Claims 1 to 7, wherein said water-soluble glass contains a boron containing compound.

9. The substrate of any one of Claims 1 to 8, wherein said glass has a dissolution rate ranging from substantially zero to 2.0 $mg/cm^2/hour$ at 38°C.

10. The substrate of any one of Claims 1 to 9, wherein said glass enables a controlled release of additives in an aqueous medium.

11. The substrate of Claim 10, wherein said additives comprise at least one metallic ion or boron.

12. The substrate of any one of Claims 1 to 11, wherein said water-soluble glass matrix comprises water-soluble glass fibres.

13. The substrate of Claim 12, wherein said glass fibres are sintered together to form non-woven mat.

14. The substrate of any one of Claims 1 to 10, wherein said water-soluble glass matrix comprises finely comminuted glass particles.

15. The substrate of Claim 14, wherein said finely comminuted glass particles are sintered together to form a porous structure.

16. The substrate of Claim 14 or 15, wherein said glass particles have an average diameter of from 15 microns to 6 mm.

17. Use of the substrate of any one of Claims 1 to 16 as an implant to replace or promote repair of damaged tissue in a patient.

18. A method to encourage growth of living tissue by providing the substrate of Claims 1 to 16.

19. Method of Claim 18, wherein said method includes the step of delivering metal ions or boron to an aqueous medium at a rate which maintains a concentration of metal ions or boron in said aqueous medium of not less than 0.01 parts per million and not greater than 10 parts per million.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
15 March 2001 (15.03.2001)

PCT

(10) International Publication Number
WO 01/18174 A2

(51) International Patent Classification[7]: C12N 5/00, A61L 27/38 // C03B 37/00, C03C 3/16

(21) International Application Number: PCT/GB00/03424

(22) International Filing Date:
7 September 2000 (07.09.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

9920974.4	7 September 1999 (07.09.1999)	GB
9927802.0	25 November 1999 (25.11.1999)	GB

(71) Applicant *(for all designated States except US)*: **GILTECH LIMITED** [GB/GB]; 9/12 North Harbour Estate, Ayr KA8 8AA (GB).

(72) Inventors; and
(75) Inventors/Applicants *(for US only)*: **GILCHRIST, Thomas** [GB/GB]; The Lodge, 67 Midton Road, Ayr KA7 2TW (GB). **HEALY, David, Michael** [IE/GB]; Midton House, By Alloway, Ayr KA7 4EG (GB).

(74) Agent: **MURGITROYD & COMPANY**; 373 Scotland Street, Glasgow G5 8QA (GB).

(81) Designated States *(national)*: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States *(regional)*: ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:
— *Without international search report and to be republished upon receipt of that report.*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/18174 A2

(54) Title: CELL GROWTH SUBSTRATE

(57) Abstract: A cell culture growth substrate comprising a water soluble glass matrix adapted to sustain growth of living cells. Preferably the substrate comprises or is coated with living cells. The water-soluble glass is advantageously phosphate based and comprises glass fibres or finely comminuted particles. The invention also relates to the use of the growth substrate as an implant to replace or promote repair of damaged tissue in a patient and to a method to encourage growth of living tissue.



Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Fig. 6



Fig. 7


Cell Activity vs Concentration for AgMg in a PBS Extraction Vehicle
Cell Activity (Optical density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 8


Cell Activity vs Concentration for AgNi in a PBS Extraction Vehicle
Cell Activity (Optical Density)
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 9


Cell Activity vs Concentration for AgZn in an MEM Extraction Vehicle
Cell activity (Optical Density)
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 10


Cell Activity vs Concentration for AgB in a PBS Extraction Vehicle
Cell activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 11


Cell Activity vs Concentration for MgCu in a PBS Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 12a


Cell Activity vs Concentration for MgCu in an MEM Extraction Vehicle
Cell Activity (Optical Density)
1.800
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 12b


Cell Activity vs Concentration for MgNi in a PBS Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 13


Cell Activity vs Concentration for MgB in a PBS Extraction Vehicle
Cell Activity(Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 14a


Cell Activity vs Concentration for MgB in an MEM Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 14b


Cell Activity vs Concentration for NiCu in a PBS EXtraction Vehicle
Cell activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 15a


Cell activity vs Concentration for NiCu in an MEM Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 15b


Cell Activity vs Concentration for NiZn in a PBS Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 16


Cell Activity vs Concentration for NiB in a PBS Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 17a

20/23


Cell Activity vs Concentration for NiB in an MEM Extarction Vehicle
Cell Activity (Optical Density)
1.800
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 17b


Cell activity vs Concentration for CuZn in an MEM Extraction Vehicle
Cell Activity (Optical Density)
2.000
1.800
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 18


Cell Activity vs Concentration for CuB in an MEM Extraction Vehicle
Cell Activity (Optical Density)
1.800
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 19


Cell activity vs Concentration for ZnB in a PBS Extraction Vehicle
Cell Activity (Optical Density)
1.600
1.400
1.200
1.000
0.800
0.600
0.400
0.200
0.000
1
2
3
4
5
6
7
8
Set Number
2d - 2d
4d - 3d

Fig. 20

United States Patent Application

COMBINED DECLARATION AND POWER OF ATTORNEY

Attorney's Docket Number _____

As a below named inventor, I hereby declare that:
My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

"Cell Growth Substrate"

the specification of which:

[c] was filed as a PCT International Application Number PCT/GB00/03424 on 7 September 2000.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with 37 CFR §1.56.

I hereby claim foreign priority documents under 35 U.S.C §119(a)-(d) or §365(b) of any foreign application(s) for patent or inventor's certificate, or §365(a) of any PCT international application which designated at least one country other than the United States, listed below and have also identified below any foreign application for patent or inventor's certificate or PCT international application having a filing date before that of the application on which priority is claimed:

PRIOR FOREIGN/PCT APPLICATION(S)

COUNTRY	APPLICATION NUMBER	DATE OF FILING	PRIORITY CLAIMED
United Kingdom	9920974.4	07.09.1999	YES
United Kingdom	9927802.0	25.11.1999	YES

I hereby claim the benefit under 35 U.S.C §120 of any United States application(s) or §365(c) of any PCT international application(s) designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of 35 U.S.C. §112, I acknowledge the duty to disclose material information as defined in 37 CFR §1.56 which become available between the filing date of the prior application and the national or PCT international filing date of this application:

PRIOR US APPLICATIONS OR PCT INTERNATIONAL APPLICATIONS DESIGNATING THE US FOR BENEFIT UNDER 25 U.S.C §120

APPLICATION No.	DATE OF FILING	PATENTED	PENDING	ABANDONED

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

Drinker, Biddle & Reath LLP
One Logan Square
18th & Cherry Streets
Philadelphia
PA 19103-6996
USA

7

Arthur H. Seidel - Registration No 15,979
Daniel A. Monaco - Registration No 30,480
John J. Marshall - Registration No 39,671
Robert E. Cannuscio – Registration No 36,469
Gregory J. Lavorgna - Registration No 30,469
Thomas J. Durling - Registration No 31,349
Joseph R. Delmaster - Registration No 38,399

I acknowledge the duty to disclose information which is material to the examination of this Application in accordance with Title 37, Code of Federal Regulations, Section 1.56(a).

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on the information and belief are believed to be true; and further that these statements were made with the knowledge that wilful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such wilful false statements may jeopardize the validity of the Application or any Patent issuing thereon.

1-00

FIRST INVENTOR

Full Name : GILCHRIST, Thomas
Residence: Ayr, Scotland
Citizenship: British (Great Britain) GBN
Post Office Address: The Lodge, 67 Midton, Ayr, KA7 2TW, United Kingdom

2-00

SECOND INVENTOR

Full Name: HEALY, David Michael
Residence: Ayr, Scotland
Citizenship: Irish (Ireland) GBN
Post Office Address: Midton House, By Alloway, Ayr, KA7 4EG, United Kingdom

Signature of First Inventor X Thomas Gilchrist Date 24 January 2002

Signature of Second Inventor X [signature] Date 24th January 2002

United States Patent & Trademark Office

Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s)_____of_____ were not present for scanning.
(Document title)

☐ Page(s)_____of_____were not present for scanning.
(Document title)

☒ ***Scanned copy is best available.*** Drawing Some Figure Dark or some very Dark